



Coverage

Approximately 80ft² to 90ft² (7.4m² to 8.4m²).

Coverage may vary due to ambient temperature, surface temperature, surface porosity, and/or application methods.

Packaging

Moisture resistant, 50lb (22.6kg) bags

Storage

1. Store bags in a cool, dry location.
2. Store away from direct contact with the ground and/or concrete.
3. Store out of direct sunlight.
4. Protect bags from weather and other damage.

Shelf Life

1 year

Color

Natural light grey or white color

Product Description

StyroGlue DryBond is a premium, dry blend, portland cement-based, polymer-modified base coat and adhesive, which is field mixed with water. StyroGlue DryBond may be used as an adhesive and base coat for AkroFlex EIF Systems and EPS foam shapes. Additionally, it may be used as a leveling coat over approved substrates.

Features

Dry Mix

Smooth Consistency

Light Color

Vapor Permeable

Polymer-modified

Benefits

Easy to mix and store; minimal waste

Easier to spread and allows thicker application

Excellent surface for light colored finishes

Allows wall assembly to breath

Increases strength, flexibility, and adhesion

Basic Uses

StyroGlue DryBond is designed for use as an adhesive or base coat for the AkroFlex EIF Systems or AkroGold DEF Systems. StyroGlue DryBond may be used as an adhesive and base coat for EPS foam shapes, as a base coat in the Omega Crack Isolation System, and as a leveling coat over approved substrates in residential and commercial wall assemblies.

Area of Use

As an adhesive to attach EPS foam to:

1. Paper-faced gypsum sheathing
2. Fiberglass mat-faced gypsum sheathing
3. Cement backer board
4. Masonry
5. Poured-in-place and/or tilt-up concrete
6. Expanded Polystyrene (EPS) foam
7. Other approved cementitious substrates

As a base coat over:

1. EPS foam board
2. Fiberglass mat-faced gypsum sheathing or cement boards
3. EPS foam shapes

As a skim coat over:

1. One coat stucco
2. Brown coat
3. Masonry
4. Poured-in-place and/or tilt-up concrete

Optional Product Upgrades/Enhancements

PRODUCT	BENEFIT
OmegaCure	Liquid accelerator to improve hydration, increase early strength/hardness, and allow cold weather application

Surface Preparation

All surfaces to receive application must be structurally sound, clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents, and cleaning solutions. Ensure that all surfaces are smooth and free of any irregularities. Repair cracks with the appropriate patching material for the existing substrate as needed. Painted or glossy surfaces must be roughened to ensure a proper bond.

Mixing

1. Add 1.75 gallons (6.6L) of potable water to a clean, 5 gallon pail.
2. Slowly add one bag of StyroGlue DryBond to the water while continuously mixing with a paddle mixer.
3. Mix thoroughly for a minimum of 3 to 5 minutes.
4. Stop mixing approximately 5 to 10 minutes and allow the material to take its initial set.
5. Material may be retempered once adding only enough water to reach the desired consistency.

Application

See the appropriate AkroFlex EIFS ICC-ES Evaluation Report for additional application instructions and requirements.

For Use as an Adhesive in an AkroFlex EIF System

1. Apply the StyroGlue DryBond to the back of the EPS insulation board with an approved notched trowel.
2. Apply the StyroGlue DryBond coated side of the insulation board to the substrate.
3. Ensure that the entire piece of insulation board has been firmly attached to the substrate.
4. Allow the StyroGlue DryBond to set for a minimum of 24 hours prior to working on the insulation board.

For Use as a Base Coat in an AkroFlex EIF System

1. Apply the StyroGlue DryBond to the substrate a minimum of 1/16" (1.6mm) thick.
2. Completely embed AkroFlex Reinforcing Mesh into this coat.
3. Trowel smooth, ensuring that no mesh is visible.

For Use as a Leveling Coat¹

1. Apply the material to the area needed to be leveled.
2. Application method will vary due to job conditions.

For Use with EPS Foam Shapes¹

1. Apply the StyroGlue DryBond to the back of the foam shape with an approved notched trowel.
2. Firmly apply the StyroGlue DryBond coated side of the foam shape to the substrate.
3. Apply the base coat to the foam shape a minimum of 1/16" (1.6mm) thick.
4. Completely embed Omega Reinforcing Mesh into this coat.
5. Trowel smooth, ensuring that no mesh is visible.

¹ When applying Omega ColorTek or other cement-based finishes over Styroglue DryBond, the use of a bonding agent or acrylic admix is required to ensure proper bond. The recommended volume of admix to be used is one to two quarts of Omega AkroLoc or two to three quarts of Omega Admix 500 per 90-lb sack of ColorTex. Omega BondCrete or AkroLoc are recommended bonders. See the applicable Omega data sheet for additional information.

Curing

Curing and/or drying time may vary due to climatic conditions, but should not take less than 24 hours at an ambient and surface temperature of 70°F (21°C) and 55% R.H. Variations in ambient and surface temperature and humidity may prolong curing and/or drying time. All freshly applied material must be protected by an approved protective system from inclement weather until fully dry and cured. It is the responsibility of the applicator to determine if the product is fully cured and/or dry prior to exposing it to rain, snow, dew, and/or any other inclement weather condition that may be detrimental to the product.

Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C).^{*} When hot, dry, or windy conditions exist, protection must be provided. The ambient and surface temperature must maintain the above requirements until fully cured (See CURING). Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully cured.

DO NOT add any other materials to the mixture of the product without written approval from Omega Products International, Inc.

DO NOT deviate in the mixing or application procedures contained in this, or any other Product Data Sheets, without written approval from Omega Products International, Inc.

DO NOT apply StyroGlue DryBond if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and/or oils.

DO NOT add any more water than prescribed.

DO NOT use a paddle mixer that exceeds 500 RPM.

DO NOT saturate the wall with water during preparation.

DO NOT leave StyroGlue unfinished.

NOTE: Failure to follow manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

^{*} To ensure proper hydration in cold weather applications (approximately 50°F to 32°F) use OmegaCure admix. Refer to OmegaCure data sheet for additional information.

Cleaning

Cleaning may be accomplished with water immediately after use.

Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

o m e g a - p r o d u c t s . c o m

Disclaimer

Omega Products International, Inc. [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the prod-

ucts are beyond the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance

Technical assistance and information is available by calling Omega Products International, Inc. at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

Warranty

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.