



Coverage

Approximately 26.5 ft² (2.1 m²) at a 1/4" thick. Coverage may vary due to ambient temperature, surface temperature, surface porosity, and/or application methods.

Packaging

50lb (22.7kg) bags

Storage

1. Store components in a cool, dry location.
2. Store away from direct contact with ground and/or concrete.
3. Store out of direct sunlight.
4. Protect bags from weather and other damage.

Shelf Life

1 year

Color

Light grey. Can be colored using Omega ColorPaks or factory colored.

Product Description

Travertino is a cementitious interior/exterior finish manufactured with a mixture of various size aggregates designed to achieve a variety of sedimentary stone appearances, such as travertine, limestone, and sandstone. Travertino can create a pitted look like that of classic Tuscan stone or can be troweled/ground to achieve a smooth stone appearance. Designs can also be carved into Travertino during application and can be used to cast special shapes. Travertino is an excellent choice to create a beautiful, warm sedimentary stone appearance with a lower cost, lower weight, and shorter lead time than real stone. Travertino is available in fine and coarse aggregate size.

FEATURES

Integral Color

Durable

Fire Resistant

Vapor Permeable

No VOCs

BENEFITS

Lasting, uniform color that resists fading or discoloration; UV resistant

Long life-cycle with minimal maintenance

Does not burn

Allows wall to naturally breath

Low odor and toxicity



Distressed



Carved



Smooth

Basic Uses

Travertino is designed for use as a decorative finish coat for a variety of substrates.

Area of Use

Travertino may be applied over the following products:

1. One coat stucco
2. Brown coat
3. Stucco
4. CMU/poured-in-place and/or tilt-up concrete/masonry
5. Approved Omega base coats and/or cementitious finishes

NOTE: When Travertino is applied over polymer-modified base coats, the use of a bonding agent or acrylic admix - may be required to ensure a proper bond and is strongly recommended. See the applicable Omega system data sheet or base coat data sheet for additional information.

NOTE: More textures may be achieved using this product. For more information contact Omega Products International.

Surface Preparation

All surfaces to receive application must be clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents, and cleaning solutions. Ensure that all surfaces are smooth and free of any irregularities. Repair all cracks with the appropriate patching material for the existing substrate. Painted or glossy surfaces should be sandblasted to expose cementitious substrate and ensure a proper bond. The use of a bonder is recommended over cementitious substrates that are four or more months old. If a bonder is not used, just prior to application, dampen all surfaces that are to receive Travertino with clean, potable water.

Mixing

1. Add 0.9 gallons (3.4L) of clean, potable water per bag to an appropriate mixing apparatus.
2. See the ColorPak Data Sheet for color mixing instructions. (Optional)
3. Turn mixer on and add Travertino.
4. Allow the material to mix for a minimum of 5 minutes.
5. Turn mixer off and allow the material to take its initial set (approximately 10 minutes).
6. Retemper the material, adding only enough water to reach the desired consistency.
7. Do not over mix.

NOTE: Apply Travertino Finish to a test area to ensure that color has been thoroughly blended prior to a full application.

Application

Travertino must be applied by a hand application method.

1. Using a hawk and trowel/red float/plastic trowel apply the material to the receiving surface, beginning at one corner and working to the next, in a single coat of uniform thickness. Allow first coat to set, but not fully dry.
2. Apply the second coat as described above and begin to trowel the applied material to a smooth finish to achieve the desired appearance (Note: A chrome or plastic trowel must be used to eliminate burning of the material). A uniform thickness must be maintained.
3. Designs or impressions may be achieved prior to the second coat fully drying.

Curing

Curing and/or drying time may vary due to climatic conditions. Drying should occur within 24 hours at an ambient and surface temperature of 70°F (21°C) and 55% R.H. When hot, dry, or windy conditions exist, light moist curing and/or protection should be provided. All freshly applied material must be protected from inclement weather until material has sufficient strength not to be damaged. Full curing strength typically occurs in approximately 28 days.

Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C).* The ambient and surface temperature must maintain the above requirements until material has sufficient strength not to be damaged (See CURING). Material that is allowed to freeze may suffer irreparable damage.

DO NOT add any other materials to the mixture of the product without written approval from Omega Products International.

DO NOT deviate in the mixing or application procedures contained in this, or any other Omega Product Data Sheets, without written approval from Omega Products International.

DO NOT apply Travertino if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and/or oils.


DO NOT add any more water than prescribed.

DO NOT saturate the wall during preparation and/or wet curing.

DO NOT use excessive amounts of water when floating and/or troweling the texture.

NOTE: Failure to follow manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

Due to job conditions beyond the control of Omega Products International, we make no warranty as to the acceptance of the final color. The actual integrally colored finish should be applied on a sample section of the project and verified or color accuracy prior to the actual application process. See Omega Products International's Technical Bulletin OP813 on Jobsite Mockups. It is expressly understood and agreed that color, texture and pigment streaking variations are inherent in all integral colored products and these conditions are not considered defects.

 To ensure proper hydration in cold weather applications (approximately 50°F to 32°F) use OmegaCure admix. Refer to OmegaCure data sheet for additional information.

Cleaning

Cleaning may be accomplished with water immediately after use.

Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

Disclaimer

Omega Products International [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manu-

facturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product

for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect.

For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance

Technical assistance and information is available by calling Omega Products International at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

Warranty

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.